



**ASTM D635-03**  
**Rate of Burning and/or Extent and Time of Burning of Plastics in a Horizontal Position**

**Client:** CLEAR FOCUS Imaging, Inc.  
60 Maxwell Court  
Santa Rosa, CA 95401

**Report No.:** 3089806SAT-001B

**Received Date:** January 27, 2006

**Test Date:** February 1, 2006

**Report Date:** May 6, 2009

**Specimen ID:** 3-7078 Punched

**Sample Description**

7 mil white/black one-way window graphic product

**Sample Dimensions:** 125mm x 13mm x 0.18mm

**Sample Preparation:** Tested as received.

**Sample Conditioning:** 73±5°F and 50±5% R.H.

**Environmental Conditions:** 69°F and 61% r.h.

**This Test Witnessed by:** n/a

*"This standard should be used to measure and describe the properties of materials, products, or assemblies in response to heat and flame under controlled laboratory conditions and should not be used to describe or appraise the fire hazard or fire risk of materials, products, or assemblies under actual fire conditions. However, results of this test may be used as elements of a fire risk assessment which takes into account all of the factors which are pertinent to an assessment of the fire hazard of a particular end use."*

**Intertek Testing Services NA, Inc.**  
16015 Shady Falls Road  
Elmendorf, Texas 78112  
Telephone: 210-635-8100 Fax: 1-210-635-8101  
e-mail: [www.intertek-etlsemko.com](http://www.intertek-etlsemko.com)

**Category Designation**

The behavior of specimens shall be classified HB (HB = horizontal burning) if,  
**a.)** There is no visible signs of combustion after the source is removed, or **b.)** The flame front does not pass the 25 mm reference mark, or **c.)** The flame front passes the 25 mm reference mark but does not reach the 100 mm reference mark, or **d.)** The flame front reaches the 100 mm reference mark and the linear burning rate does not exceed 40 mm/min for specimens having a thickness between 3 and 13 mm or 75 mm/min for specimens having a thickness less than 3 mm.

**Summary of Test Method**

A bar of the material to be tested is supported horizontally at one end. The free end is exposed to a specified methane gas flame for 30s. Elapsed time (t) and Burned length (L) are measured and reported if the specimen burns between 25mm and 100mm. An average burning rate is reported for a material if it burns to the 100-mm mark from the ignited end.

**TEST RESULTS**

<b>Specimen</b>	<b>Did Flame Reach 25mm (Y/N)</b>	<b>Did Flame Reach 100mm (Y/N)</b>	<b>Elapsed Time* (sec)</b>	<b>Burned Length* (mm)</b>
1	No	No	N/A	N/A
2	No	No	N/A	N/A
3	No	No	N/A	N/A
4	No	No	N/A	N/A
5	No	No	N/A	N/A
6	No	No	N/A	N/A
7	No	No	N/A	N/A
8	No	No	N/A	N/A
9	No	No	N/A	N/A
10	No	No	N/A	N/A
<b>Average</b>			N/A	N/A

\* This data is not available because the flame did not reach the 25mm reference mark.




**Conclusion:**

**This specimen meets the HB classification requirements.**

*This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Only the Client is authorized to copy or distribute this report and then only in its entirety. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.*


This report consists of three pages.



\_\_\_\_\_  
Servando Romo  
Project Manager

May 6, 2009

Reviewed and approved:



\_\_\_\_\_  
C. Anthony Peñaloza  
Flammability Testing Team Leader

May 6, 2009

**Intertek**